

PRODUCT DESCRIPTION

Epiglass Epoxy Solvent has been formulated for use with Epiglass HT9000 Epoxy Resin in surface preparation and equipment cleaning. Used for wiping down surfaces prior to application of resin, glue or fairing mixes.

PRODUCT INFORMATION

Colour	YTA901-Clear
Specific Gravity	0.851
Typical Shelf Life	2 yrs
VOC (As Supplied)	851 g/ltr
Unit Size	500 ml 5 Lt

DRYING/OVERCOATING INFORMATION

Drying

Overcoating Substrate Temperature

Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
---------------	-----	-----	-----	-----	-----	-----	-----	-----

APPLICATION AND USE

Preparation	<p>GRP: Wipe down surface after sanding, using several clean cloths to ensure all contaminants are removed. For interior gelcoat the surface must be thoroughly degreased before sanding (to remove the wax layer) and after.</p> <p>WOOD: Remove all sanding dust and wipe with Epiglass Epoxy Solvent before any job. When sealing wood with Epiglass HT9000, dilute 100% with Epiglass Epoxy Solvent to saturate the substrate. Subsequent coats should be applied with the thinner content reduced to 50% and 25% respectively. Sealer should be used on all structural wood work and planking. Ensure diluted layers are fully cured to allow the solvent to evaporate. Full saturation should be achieved by the fourth (unthinned) application.</p> <p>METAL: Wipe the surface with Epiglass Epoxy Solvent before priming. Use several clean cloths.</p>
Method	When using for surface wipe down, turn the cloth frequently to avoid re-applying residues. Wear a dust mask when sanding Epiglass HT9000 epoxy.
Hints	Ventilation and Humidity Control Ensure adequate ventilation during use.
Some Important Points	Do not wash bare glass fibre laminates with solvent. Do not thin Epiglass HT9000 for use on bare glass fibre laminates.
Compatibility/Substrates	For use with Epiglass HT9000 Epoxy Resin only. Will efficiently clean equipment used for preparation and/or application of Epiglass HT9000. Do not leave epoxy resin to cure before attempting to remove it. Always ensure the resin and curing agent of Epiglass HT9000 have been carefully mixed at the correct 4:1 ratio by volume.

Recommended DFT

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage **GENERAL INFORMATION:**

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Epiglass Epoxy Solvent to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Epiglass Epoxy Solvent should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Epiglass Epoxy Solvent cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office
International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region
International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region
International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region
International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region
International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region
International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000115
Issue Date: 4-Sep-2004
Supersedes: 14-Feb-2003