

PRODUCT DESCRIPTION

A versatile epoxy resin system, suitable for a wide variety of uses, such as sheathing, laminating, filling and fairing, and gluing, on boats of all types. In addition to the high strength and durability associated with epoxy resins, this unique and easy-to-use formula offers many special features:

- * Solvent free and low odour ensuring a cleaner working environment.
- * Improved workability to adapt to varying environments
- * Low viscosity for ease of mixing and wet out
- * Fast hardener allowing a short time between re-application/sanding

From a background of thirty years of experience in Australia and New Zealand, International now offers a tried and tested multipurpose epoxy system for professional and DIY use.

PRODUCT INFORMATION

Colour	YAA900-Clear
Finish	Gloss
Specific Gravity	1.01
Volume Solids	100%
Mix Ratio	4:1 by volume , Converter/Curing Agent - YAA908 Fast Curing Agent
Typical Shelf Life	2 yrs
VOC (As Supplied)	0 g/ltr
Unit Size	0.6 kg 1.2 kg

DRYING/OVERCOATING INFORMATION

Drying

	10°C	15°C	25°C
Pot Life	35mins	25mins	14mins

Note: Pot life reduces as temperature and mix volume increases. Thin Film Working Time: 10°C - 4 hrs; 15°C - 2.5 hrs; 25°C - 1.5 hrs.

Overcoating Substrate Temperature

Overcoated By	10°C		15°C		25°C	
	Min	Max	Min	Max	Min	Max

Note: Due to the variety of film builds, and hence different cure times, it is not possible to give specific overcoating times. Overcoating HT9000 with itself: HT9000 resin and/or HT9000 glue/filler mixes may be overcoated with themselves or each other whilst they are still wet or tacky. After this period, overcoating can be carried out whilst the mixes are green (i.e. soft to the fingernail). Once the products feel hard to a fingernail they should be washed down to remove any amine bloom and sanded well. Overcoating with other products: Overcoating HT9000 resin or HT9000 Filler/Glue mixes with any solvent containing paints should not be carried out until the surfaces can be sanded using 80-120 grit paper.

APPLICATION AND USE

Preparation

GRP: Thoroughly abrade using 80-120 grade paper. Degrease with Epiglass Epoxy Solvent. Ensure surface is dry before application of the epoxy. New laminates must be at least one month old before application of Epiglass HT9000. New laminates should also be cleaned first with Yacht Line Super Cleaner to remove mould release agents, silicones and grease.

WOOD: Moisture content of the wood should be below 12%. For higher moisture content the timber must be allowed to dry prior to application of Epiglass HT9000. Abrade with 80-120 grade (grit) paper. Sand across the grain with 40-60 grade paper for good adhesion when gluing. Wipe down with Epiglass Epoxy Solvent. Epoxy resin should not be used for structural work with oily timbers. For smaller repairs on oily timbers, abrade as per above recommendation and degrease with acetone. Allow solvent to evaporate.

METAL: To ensure a good physical 'key' on the surface, remove all surface contaminants by abrading, grit blasting or grinding to expose bright metal. Wipe down with Epiglass Epoxy Solvent. Apply the epoxy resin as soon as possible after surface has been prepared, to prevent de-oxidisation. For Aluminium/Bronze/Lead, better adhesion will be achieved by sanding the resin mix into the surface using wet or dry paper. Hard anodised aluminium alloy must be removed.

Method	Apply to a surface pre-primed with a thin layer of resin mix. Techniques will vary depending on the job in hand. Refer to the Epiglass Epoxy Resin Guide. For Coating and Sheathing, apply a first primer coat and then subsequent coats with a brush or roller. A glue brush can be used for Gluing or a spatula which can also be used for Fillet Bonding. Use a spreader for Filling and Fairing applications. When using Epiglass HT9000 as a wood sealer, or even when sheathing wood, it is beneficial to saturate the wood with a 100% diluted resin mix. This will further improve adhesion. Diluted layers must be fully cured prior to application of subsequent (unthinned) coats. A hot air gun or alternatively a hair dryer can be used to warm the epoxy and shorten its cure time, whilst promoting good penetration of most wood types without the need for solvent addition. Pot life reduces as temperature and mix volume increases Ultra violet light will break down the epoxy over time and the completed work should therefore be painted or varnished. A range of International primers, undercoats and finishes are compatible with Epiglass HT9000. Refer to the International Boat Painting Guide for an introduction on the products and their use.
Hints	<p>Mixing Always measure accurately by volume to the 4:1 ratio. Epiglass Dispensing Pumps are calibrated to supply the 4:1 mix ratio. First few strokes could supply aerated resin and have an irregular flow. Ensure correct volume is supplied through the pumps before mixing for use (i.e consistent flow of resin). Add curing agent to the base in a mixing pot and stir slowly for approximately 2 minutes. Use a clean plastic container (alternatively metal) when mixing Epiglass HT9000 and mix small amounts at any one time, to prevent heat build-up. Pour the Epiglass mix into a flat roller tray to allow longer working time. IMPORTANT: Avoid using a glass container due to the risk of heat build up. If the epoxy resin starts to exotherm (build up heat) the container should be moved outdoors. Avoid breathing the fumes. Carefully blend in any additive powders chosen until the desired consistency is achieved. Further details on additives and their use can be found in the Epiglass Epoxy Resin Guide. Mix only as much as you can use in the stated pot life.</p> <p>Thinner YTA901 Epiglass Epoxy Solvent Cleaner YTA901 Epiglass Epoxy Solvent Other Use glue powder in all filler, fairing and filleting mixes to prevent sagging. Curing The total cure time varies depending on hardener used (fast, standard or slow), volume mixed, temperature and the shape of the mixing cup. The pot lives recorded in this datasheet are based on a 100g resin/hardener mix.</p>
Some Important Points	Do not apply below 10°C. Woods such as teak and iroko are rich in natural oils, and so not usually suited to overcoating except with specialist varnishes such as International Perfection for Teak or Schooner. An amine blush may form on the surface of the Epiglass HT9000 as it cures, particularly in cold, damp conditions. The cured Epiglass HT9000 should therefore be fresh water washed with a 3M Scotchbrite pad to remove any amine blush before proceeding with the application of varnish, undercoat, etc. Dry the surface with paper towels. Do not apply over conventional (one-pack) coatings. Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 10°C and maximum 35°C. Substrate temperature should be minimum 10°C and maximum 35°C.
Compatibility/Substrates	Epiglass HT9000 will adhere to most substrates which have been thoroughly prepared, with the exception of thermoplastics such as PVC and polypropylene. Do not use on GRP which is not fully cured. Use the fast curing agent when a short time before re-application/sanding is required eg: Coating, Sheathing and Gluing. For longer working time use standard or slow curing agent (see individual datasheets). Do not use for structural work with oily timbers.
Number of Coats	Variable
Coverage	(Theoretical) - 13.75 (m ² /lt) 7.5-20 m ² /lt. Varies depending on usage.
Recommended DFT	
Application Methods	Brush, Roller , DO NOT SPRAY

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Epiglass HT9000 to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: Epiglass HT9000 should be kept in securely closed containers during transport and storage.</p>
Safety	<p>GENERAL: Avoid contact with skin and eyes. Epiglass HT9000 can cause dermatitic skin reactions. Always use gloves and goggles and keep skin protected with overalls. Any accidental skin contact should be immediately washed off with soap and water. Do not eat, drink or smoke in mixing or application areas. Wear suitable respiratory protective equipment. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p>

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Epiglass HT9000 cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000335
Issue Date: 4-Sep-2004
Supersedes: 12-Aug-2003