

PRODUCT DESCRIPTION

A conventional marine wood filler for use above the waterline. It is ideal for filling screwholes and small cracks in paintwork around seams, where a fine cosmetic finish is required.

PRODUCT INFORMATION

Colour	YAA041-Off White
Specific Gravity	1.90
Typical Shelf Life	2 yrs
Unit Size	170 ml 500 ml

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		15°C		23°C		35°C	
Sandable	8hrs		4hrs		2hrs		1hrs	

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Pre-Kote	48hrs	-	36hrs	-	24hrs	-	12hrs	-
Yacht Primer	48hrs	-	36hrs	-	24hrs	-	12hrs	-

APPLICATION AND USE

Preparation	Surface must be clean and dry prior to application of Interfill 100. Remove loose material. To ensure optimum adhesion, prime with UCP, Yacht Primer, Interprotect or thinned varnish first. Sand any primer or undercoat that has been applied more than 3 days previously (280-320 grade paper).
Method	Remove dust with a dust wipe. Fill to a level slightly above the surrounding area. When fully dry sand smooth and seal with remaining coats of one-pack primer or varnish as appropriate.
Hints	<p>Tinting Interfill 100 may be tinted with small additions of Interstain or International yacht enamels.</p> <p>Cleaner YTA800 Thinners No.1</p> <p>Other Remove the amount you plan to use and re-seal the pack to avoid skinning.</p>
Some Important Points	Not suitable for underwater use. Do not apply thicker than 2 mm per application. Do not overcoat with any two-pack products. Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 7°C and maximum 35°C. Substrate temperature should be minimum 7°C/45°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all types of wood. Only overcoat with one-pack paints.
Coverage	(Theoretical) - Variable.
Recommended DFT	
Application Methods	Use a spreader or filling knife.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interfill 100 to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Interfill 100 should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Interfill 100 cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriental House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000086
Issue Date: 4-Sep-2004
Supersedes: 14-Feb-2003