

PRODUCT DESCRIPTION

Interlux Super is an easy to apply, full gloss conventional yacht enamel designed to resist the effects of the marine environment.

* Traditional Yacht Enamel for all applications

* Can be used on all suitably prepared substrates

PRODUCT INFORMATION

Colour	YLB000-Snow White
Finish	Gloss
Specific Gravity	1.2
Volume Solids	56%
Typical Shelf Life	2 yrs
VOC (As Supplied)	302 g/ltr
Unit Size	750 ml 2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		15°C		23°C		35°C	
Touch Dry [ISO]	10hrs		6hrs		2hrs		1hrs	

	Overcoating							
	Substrate Temperature							
Overcoated By	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Interlux Super	36hrs	4days	24hrs	3days	16hrs	2days	6hrs	1days

APPLICATION AND USE

Preparation	<p>PREVIOUSLY PAINTED SURFACES:</p> <p>In Good Condition: Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.</p> <p>In Poor Condition: Remove all previous coatings and prime the substrate.</p> <p>PRIMING: All preparation for bare substrates is covered on the appropriate primer datasheet.</p> <p>BARE WOOD: Prime with Yacht Primer or UCP.</p> <p>STEEL: Prime with Yacht Primer or Interprotect.</p> <p>ALUMINIUM: Prime with Etch Primer followed by either Yacht Primer or Interprotect.</p> <p>GRP: Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 180-220 grade paper. No priming necessary.</p> <p>ALL SUBSTRATES: Use Pre-Kote undercoat.</p>
Method	Sand the undercoat smooth with 320-400 grade (grit) wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.
Hints	<p>Mixing Stir well before use.</p> <p>Thinner YTA800 Thinners No.1</p> <p>Cleaner YTA800 Thinners No.1</p> <p>Ventilation and Humidity Control Apply in dry, well ventilated conditions.</p> <p>Other For lighter colours, mix the first coat of finish 50:50 with the undercoat to improve the depth of colour and opacity. For best results when applying by roller, smooth off with a pad or brush. Avoid applying late in the evening as condensation can cause a loss of gloss overnight.</p>
Some Important Points	Interlux Super may discolour if used at temperatures above 80°C. Product temperature should be minimum 15°C/60°F and maximum 30°C/86°F. Ambient temperature should be minimum 5°

C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.

Compatibility/Substrates	Use over suitably prepared and undercoated surfaces or existing paint schemes. Not suitable for permanently immersed surfaces.
Number of Coats	1-2
Coverage	(Theoretical) - 12.00 (m ² /lt) by brush
Recommended DFT	42 microns dry
Recommended WFT	75 microns wet
Application Methods	Brush, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interlux Super to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Interlux Super should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Interlux Super cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office
International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region
International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region
International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region
International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region
International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region
International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000032
Issue Date: 4-Sep-2004
Supersedes: 20-Feb-2003