

PRODUCT DESCRIPTION

Interprime Accelerator is used in Interprime 850 and Interprime 880 to promote quicker sanding in cooler weather.

PRODUCT INFORMATION

Colour	YPA002-Clear
Specific Gravity	0.9
Volume Solids	35%
Typical Shelf Life	2 yrs
VOC (As Supplied)	590 g/ltr
Unit Size	250 ml

DRYING/OVERCOATING INFORMATION

Drying

Overcoating Substrate Temperature

Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
---------------	-----	-----	-----	-----	-----	-----	-----	-----

APPLICATION AND USE

Method	At temperatures of or below 20°C/70°F, add 2.5% by volume of Interprime Accelerator to Interprime 880 after induction. 45 ml (3 capfuls) of Interprime Accelerator should be added to a 2 litre mix of Interprime 880. At temperature of or below 20°C/70°F, add 10-15% by volume of Interprime Accelerator to Interprime 850 after induction. 100-150 ml (approx. 7-10 capfuls) of Interprime Accelerator required per 1 litre mix of Interprime 850.
Hints	<p>Mixing When using Interprime Accelerator in Interprime 850 or Interprime 880, always mix the Base with the Curing Agent in the appropriate ratio and allow the proper induction time before adding in the correct amount.</p> <p>Thinning Reduce if necessary; the amount of Interprime Accelerator added counts towards the overall percentage reduction.</p>
Some Important Points	Accelerator is not necessary or recommended above 20°C/70°F. NEVER add more than 2.5% by volume of Interprime Accelerator to Interprime 880.
Compatibility/Substrates	Interprime Accelerator is NOT compatible with Urethane Topcoats and Epoxy Fillers including Interfill 835. Suitable for use with Interprime 850 and Interprime 880 only. Do not use in Interprime 820.

Recommended DFT

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interprime Accelerator to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: Interprime Accelerator should be kept in securely closed containers during transport and storage.</p>
----------------	---

Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Interprime Accelerator cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000247
Issue Date: 14-Feb-2003
Supersedes: 28-Nov-2002