

PRODUCT DESCRIPTION

Product specifically developed for the economical protection of steel. This tough, non-cracking coating offers protection against rust and is ideal for Narrowboat Blacking.

- * Economical protection for Steel
- * Tough, non-cracking formulation
- * Chemically resistant to mild acids and alkalis

PRODUCT INFORMATION

Colour	YMA741-Black
Finish	Matt
Specific Gravity	1.0
Volume Solids	47%
Typical Shelf Life	2 yrs
Unit Size	2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	24hrs	8hrs	8hrs	8hrs

	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Intertuf 16	24hrs	-	8hrs	-	8hrs	-	8hrs	-

APPLICATION AND USE

Preparation	<p>EXTERIOR HULL COATING: STEEL: Remove any rust with 60-80 grade abrasive paper and remove all dust. PREVIOUSLY PAINTED SURFACES: Sand surface with 120-150 grade (grit) paper and remove all dust.</p>
Method	Apply 2-3 coats (spray) or 4-5 coats (brush).
Hints	<p>Mixing Stir well before use. Thinner YTA800 Thinners No.1 Cleaner YTA800 Thinners No.1 Ventilation and Humidity Control Apply in a well ventilated area. Airless Spray Pressure: 176-210 bar. Tip Size: 1880-2680. Other Leave until completely dry (min. 3 days @ 15°C).</p>
Some Important Points	Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for Steel and Painted Surfaces (Holding Primers). Not suitable for GRP or Alloy.
Number of Coats	2-3 (spray); 4-5 (brush)
Coverage	(Theoretical) - 8.00 (m ² /lt) by brush; 3.5m ² /lt (spray).

Recommended DFT	100 microns dry / 53 microns dry
Recommended WFT	215 microns wet / 110 microns wet
Application Methods	Airless Spray, Brush, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Intertuf 16 to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Intertuf 16 should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Intertuf 16 cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriental House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000104
Issue Date: 13-Nov-2002
Supersedes: 11-Oct-2001