

PRODUCT DESCRIPTION

Trilux Prop-O-Drev is a hard antifouling that is specially formulated for use on outdrives, outboard legs, propellers and sterngear.

- * Aerosol spray is ideal for painting awkward shapes and difficult to reach areas.
- * Quick and easy application saves you time and effort.
- * Suitable for use on aluminium and stainless steel.

PRODUCT INFORMATION

Colour	YBA768-Grey, YBA798-Black
Finish	Matt
Specific Gravity	0.8
Volume Solids	9% average
Typical Shelf Life	2 yrs
Unit Size	500 ml

DRYING/OVERCOATING INFORMATION

	Drying			
	0°C	15°C	23°C	35°C
Immersion	3hrs	3hrs	3hrs	3hrs

	Overcoating							
	Substrate Temperature							
	0°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Trilux Prop-O-Drev	30mins	ext	30mins	ext	30mins	ext	30mins	ext

APPLICATION AND USE

Preparation	Prime bare metal and factory enamelled surfaces with 2 coats of VC Prop-O-Drev Primer. This is essential on aluminium and alloy as Trilux Prop-O-Drev is NOT suitable for direct application. For best results on previously antifouled surfaces, remove existing paintwork. Alternatively, abrade with wet 240 grade paper.
Method	Spray sparingly 10-15 cm (4-10") from the surface. Apply a minimum of 3 coats, allowing 30 mins between coats.
Hints	<p>Mixing Shake can thoroughly.</p> <p>Thinner YTA600 VC General Thinner.</p> <p>Cleaner YTA600 VC General Thinner.</p> <p>Other Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to apply the correct thickness.</p>
Some Important Points	To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product temperature should be minimum 0°C and maximum 35°C. Ambient temperature should be minimum 0°C/32°F and maximum 35°C/95°F. Substrate temperature should be minimum 1°C above dew point and maximum 35°C.
Compatibility/Substrates	Suitable for use on all substrates including suitably primed Aluminium/Alloy and Zinc-sprayed metals. Also suitable for factory enamelled finishes.
Number of Coats	3 minimum

Coverage

(Theoretical) - Approx. 1 can per medium-sized outdrive.

Recommended DFT**TRANSPORTATION, STORAGE AND SAFETY INFORMATION****Storage****GENERAL INFORMATION:**

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Trilux Prop-O-Drev to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Trilux Prop-O-Drev should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Contains biocides. Antifoulings should only be wet sanded. Never dry sand or burn-off old antifoulings. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Trilux Prop-O-Drev cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

 and International are registered trademarks of Akzo Nobel.

Regional AddressesHead Office

International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000273
Issue Date: 13-Jan-2004
Supersedes: 12-Jan-2004