

PRODUCT DESCRIPTION

VC Prop-O-Drev Primer is specially formulated for use with Prop-O-Drev on outdrives, outboard legs, propellers and sterngear.

* Aerosol ideal for painting awkward shapes

It offers excellent adhesion to properly prepared metal and factory enamelled surfaces.

PRODUCT INFORMATION

| | |
|--------------------|-------------|
| Colour | YPA688-Grey |
| Finish | Matt |
| Specific Gravity | 0.8 |
| Volume Solids | 9% |
| Typical Shelf Life | 2 yrs |
| VOC (As Supplied) | 691 g/l |
| Unit Size | 300 ml |

DRYING/OVERCOATING INFORMATION

| | Drying | | | | | |
|-----------------|--------|--|------|--|--------|--|
| | 5°C | | 15°C | | 23°C | |
| Touch Dry [ISO] | 2hrs | | 1hrs | | 30mins | |

| | Overcoating | | | | | |
|-----------------------|-----------------------|-------|------|-------|------|-------|
| | Substrate Temperature | | | | | |
| Overcoated By | 5°C | | 15°C | | 23°C | |
| | Min | Max | Min | Max | Min | Max |
| Trilux Prop-O-Drev | 3hrs | 6mths | 2hrs | 6mths | 1hrs | 6mths |
| VC Prop-O-Drev Eco | 3hrs | 6mths | 2hrs | 6mths | 1hrs | 6mths |
| VC Prop-O-Drev Primer | 3hrs | 6mths | 2hrs | 6mths | 1hrs | 6mths |

Note: If maximum overcoating time is exceeded, sand the surface with dry 240 grade wet and dry paper.

APPLICATION AND USE

| | |
|---------------------------------|--|
| Preparation | Shield nearby areas and clean surface with VC General Thinner. Sand with 120 grade wet and dry paper, used dry, wiping clean with VC General Thinner. |
| Method | Spray 10-25 cm (4-10") from the surface. Apply second coat following overcoating times specified. |
| Hints | Mixing Shake can thoroughly. Cleaner YTA600 VC General Thinner. |
| Some Important Points | Product temperature should be minimum 0°C and maximum 35°C. Ambient temperature should be minimum 0°C/32°F and maximum 35°C/95°F. Substrate temperature should be minimum 1° C above dew point and maximum 35°C. |
| Compatibility/Substrates | For use on Aluminium/Alloy, Zinc-sprayed Surfaces and Lead. Also suitable for factory enamelled finishes. |
| Number of Coats | 2 |
| Coverage | (Theoretical) - 3.33 (m ² /lt) 1 m ² /300 ml can. |
| Recommended DFT | |
| Application Methods | Aerosol can |

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of VC Prop-O-Drev Primer to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

VC Prop-O-Drev Primer should be kept in securely closed containers during transport and storage.

Safety


GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of VC Prop-O-Drev Primer cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

 and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint LLC
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000106
Issue Date: 10-Mar-2005
Supersedes: 22-Dec-2004