

#### PRODUCT DESCRIPTION

Veridian represents a breakthrough in coatings technology, providing a two part (Tie Coat and Top Coat) biocide-free fouling release system.

- \* Two-pack, ultra-low surface energy Top Coat
- \* High gloss finish by brush or roller
- \* Contains no biocide; may be used in areas where biocide use is forbidden
- \* Foul release coating that is easy to clean and increases boat speed and lowers fuel consumption
- \* Easy clean coating for outdrives and outboards
- \* Self cleaning coating on propellers (if used frequently)

#### PRODUCT INFORMATION

<b>Colour</b>	YMA162-Clear . Veridian for Outdrives and Outboards available in white and clear Top Coat only, giving white, clear and grey scheme options. See separate datasheet for details of White/Colours Top Coats.
<b>Finish</b>	Gloss
<b>Specific Gravity</b>	1.0
<b>Volume Solids</b>	75%
<b>Mix Ratio</b>	3:1 by volume , Converter/Curing Agent - YMA168
<b>Typical Shelf Life</b>	2 yrs
<b>Unit Size</b>	750 ml (Clear scheme kit only). Pack consists of 3 x 375 ml cans joined together. 250 ml Tie Coat, 375 ml Top Coat Base and 125 ml Top Coat Curing Agent. 2.2 Lt

#### DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	8hrs	4hrs	2hrs	1.5hrs
Immersion	4days	2days	1days	1days
Pot Life	4hrs	4hrs	4hrs	4hrs

**Note:** Pot Life: May be extended to 24 hours, for pad areas, if thinned 10% with Thinners No.3. Drying times at 10°C: Pot Life 4hrs, Touch Dry 5hrs and Immersion 3 days minimum. Max. Immersion Times are as follows: 5-35°C/40-95°F - 3 mths

	Overcoating Substrate Temperature							
	5°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max

**Note:** Clear Top Coat should be applied in one coat only.

#### APPLICATION AND USE

<b>Preparation</b>	<p>Must be applied over Veridian Tie Coat only. Follow overcoating times specified.</p> <p><b>DAMAGED VERIDIAN SCHEME::</b></p> <p><b>Small scratches or imperfections:</b> Tie Coat is not required for small scratches where the old Tie Coat is intact. Wipe the surface with Thinners No. 3, allow to dry and immediately apply Veridian Top Coat.</p> <p><b>Larger areas of damage::</b> Abrade the exposed Tie Coat with 80 grade paper and wipe clean with Thinners No. 3 prior to applying Tie Coat and Top Coat.</p> <p><b>Damage down to bare metal or wood::</b> Reapply the full scheme, as per the procedure specified for the particular substrate.</p> <p><b>Removal of the Veridian scheme from metal surfaces can be achieved by using standard DIY paint strippers (propellers only):</b> This type of paint stripper is not suitable for use on fiberglass.</p>
--------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>Method</b>	The clear Top Coat can be applied in one application at the specified minimum 250 microns WFT. Total film thickness of the Top Coat is the most important factor in the success of the Veridian system. Note that this is quite a high film build and that the product will spread thinner
---------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

than the wet film thickness quoted.

## Hints

**Mixing** Stir contents of each part prior to mixing. Add Curing Agent to the Base, stir and leave for 10 minutes to allow bubbles to disperse.

**Thinner** YTA910, YTA085 Thinners No.3 Thinner 910

**Roller** High density foam roller is recommended for best application. If a mohair roller is used, the coating should be laid off with a brush, using vertical strokes. This will optimise the flow of the coating, and prevent sagging and orange peel.

**Other** For HVLP spray application: Reduce viscosity to 30 seconds, BS4 flow cup with Thinner 910. Pressure: Wall - 80 psi; Cup - 8 psi; Tip - 5 psi. Tip Size: 1.0 mm. If spray application is to be used, ensure the boat is tented to prevent contaminating other paint applications with silicone. 250 microns (10 mils) wet is ESSENTIAL for performance. Use paint calculator on the boater's guide for the number of tins required for your hull shape. The coating will not act as an antifouling as it does not contain biocides. The coating will allow easy cleaning of the hull with a cloth or sponge. The hull should be cleaned at least once a month; more often in high fouling areas. Lightly wiping over the surface with a sponge or a soft cloth is all that is needed to dislodge even the most stubborn fouling. Abrasives, chemical cleaners and high-pressure water washers are not recommended as they will damage the surface of the coating. Propellers coated with Veridian will self-clean if they are used frequently and hence heavy fouling is not allowed to accumulate. Static items (e.g outdrive coatings) can be quickly and easily cleaned by lightly wiping off any fouling with a soft cloth at regular intervals.

## Some Important Points

Do not use in high wind. The coating will not act as an antifouling as it does not contain biocides. Do not abrade or use abrasive cleaners as the coating is easily damaged. Do not use high pressure water wash. Do not immerse before the stated minimum times or the adhesion of the system will be very poor and the system will damage easily. Veridian must be cleaned on a regular basis to maintain the surface free from fouling. In particular, ensure shell fouling is removed at an early stage, when it will be only very weakly attached to the surface and will be easy to remove. Some discolouration of the finish coat is expected if shell fouling is left on the surface. Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.

## Compatibility/Substrates

Must be applied over itself or Veridian Tie Coat only. The Veridian Scheme is not suitable for use on bronze or mixed alloy propellers, or on stainless steel.

## Number of Coats

1 only

## Coverage

(Theoretical) - 3.50 (m<sup>2</sup>/lt)

## Recommended DFT

## Recommended WFT

250 microns wet minimum

## Application Methods

Brush, HVLP Spray, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

### Storage

#### GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Veridian to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

#### TRANSPORTATION:

Veridian should be kept in securely closed containers during transport and storage.

### Safety

**GENERAL:** Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

**DISPOSAL:** Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Veridian cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

### IMPORTANT NOTES

*The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

Head Office  
International Paint Ltd  
P O Box 20980  
Oriental House

European Region  
International Paint Ltd  
Stoneygate Lane  
Felling, Gateshead

Asia Region  
International Paint Singapore  
(Pte) Ltd  
449 Tagore Industrial Avenue

Australasia Region  
International Paint  
115 Hyde Road  
Yeronga, Brisbane

North America Region  
International Paint Inc  
2270 Morris Avenue  
Union

South America Region  
International Paint  
Rod Rap tavares, KM 18.5  
Predio Administrativo 11

16 Connaught Place  
London W2 2ZB  
United Kingdom  
tel: +44 (0) 171 479 6000  
fax: +44 (0) 171 479 6500

Tyne & Wear NE10 0JY  
United Kingdom  
tel: +44 (0) 191 469 6111  
fax: +44 (0) 191 438 3977

01-03 Hong Joo Industrial  
Building  
Singapore 787820  
tel: +65 6453 1981  
fax: +65 6453 1778

Queensland 4104  
Australia  
tel: +61 (0) 7 3892 8866  
fax: +61 (0) 7 3892 4287

New Jersey 07083  
USA  
tel: +1 (0) 908 686 1300  
fax: +1 (0) 908 686 8545

Butanta CEP 05577-300  
Sao Paulo, Brazil  
tel: +55 (0) 11 3789 2000  
fax: +55 (0) 11 3789 2200



Ref: 05000206  
Issue Date: 28-Dec-2004  
Supersedes: 13-Feb-2003