

PRODUCT DESCRIPTION

A mahogany wood stain for staining brightwork and restoring colour to faded timber.

* Penetrating formulation

* Resistant to fade for interior and exterior use

PRODUCT INFORMATION

Colour	YAA825-Mahogany
Finish	Low sheen
Specific Gravity	0.95
Volume Solids	11%
Typical Shelf Life	2 yrs
VOC (As Supplied)	521 g/lit
Unit Size	375 ml

DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	3hrs	2hrs	1hrs	30mins

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Dex 1+2	4hrs	-	3hrs	-	2hrs	-	1hrs	-
Goldspar	4hrs	-	3hrs	-	2hrs	-	1hrs	-
Goldspar Satin	4hrs	-	3hrs	-	2hrs	-	1hrs	-
Interstain	4hrs	-	3hrs	-	2hrs	-	1hrs	-
Original	4hrs	-	3hrs	-	2hrs	-	1hrs	-
Schooner	4hrs	-	3hrs	-	2hrs	-	1hrs	-

Note: For all two-pack products, including Epiglass HT9000, allow 2-3 days before overcoating.

APPLICATION AND USE

Preparation	Sand with 80-180 grade (grit) paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat. Preserve, if required, with Intertox.
Method	Apply one or more coats as required for colour. Finish with International Varnishes or Epiglass HT9000 Epoxy Resin.
Hints	Mixing Stir or shake thoroughly. Thinner YTA800 Thinners No.1 Cleaner YTA800 Thinners No.1
Some Important Points	Product temperature should be minimum 10°C and maximum 35°C. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all types of wood. Only use on bare wood. Can be mixed with all International varnishes to give a darker tint. Interstain can also be used with Interfill 100 Wood Filler.
Number of Coats	1-3 as required

Coverage (Theoretical) - 13.00 (m²/lt) 8-18 m²/lt depending on porosity of wood.

Recommended DFT

Application Methods Brush . Also cloth and pad

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage **GENERAL INFORMATION:**
Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interstain to be realised ensure that between use the container is firmly closed and the temperature is between 5° C/40°F and 35°C/95°F. Keep out of direct sunlight.
TRANSPORTATION:
Interstain should be kept in securely closed containers during transport and storage.

Safety **GENERAL:** Read the label safety section for Health and Safety Information, also available from our Technical Help Line.
DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.
Remainders of Interstain cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*
X and International are registered trademarks of Akzo Nobel.

Regional Addresses

<u>Head Office</u> International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500	<u>European Region</u> International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne & Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977	<u>Asia Region</u> International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778	<u>Australasia Region</u> International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287	<u>North America Region</u> International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545	<u>South America Region</u> International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200
--	--	---	--	--	--



Ref: 05000095
Issue Date: 14-Feb-2003
Supersedes: 28-Nov-2002