

PRODUCT DESCRIPTION

Schooner is a traditional tung-oil based gloss yacht varnish for classic yachts, suitable for all internal and external wood. It contains UV filters to screen the sun's damaging rays for remarkable durability.

- * Easy application
- * Deep, rich gloss
- * Warm golden colour
- * Excellent UV protection
- * For interior and exterior use.

Schooner has excellent water resistance, silky application and superior self-leveling properties.

PRODUCT INFORMATION

Colour	YVA086-Yellow/Amber
Finish	High Gloss
Specific Gravity	0.89
Volume Solids	48%
Typical Shelf Life	2 yrs
VOC (As Supplied)	411 g/ltr
Unit Size	375 ml 750 ml 2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	10°C		15°C		23°C		35°C	
Touch Dry [ISO]	3hrs		2.5hrs		2hrs		1hrs	

	Overcoating							
	Substrate Temperature							
	10°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Schooner	16hrs	1mths	14hrs	1mths	12hrs	1mths	8hrs	1mths

APPLICATION AND USE

Preparation

PREVIOUSLY VARNISHED WOOD:

In Good Condition: Clean with Yacht Line Super Cleaner. Sand smooth with 280-320 grade paper. Remove sanding dust with a dust wipe.

In Poor Condition: Remove all previous coatings.

BARE WOOD: Sand smooth with 80-180 grade paper and then 280 grade paper. Clean surface by brushing, dusting or wiping. If wiping with solvent then allow to dry completely before applying first coat of varnish.

Method

Pour the amount you expect to use in a separate container. Avoid using direct from the can. Strain it through a paint strainer to ensure there is no contamination. **PREVIOUSLY VARNISHED WOOD:** Apply 2-4 full coats, until a satisfactory finish is achieved. Sand between coats using 320-400 grade paper. Remove dust with a dust wipe. **BARE WOOD:** Apply the first coat thinned 10% with Thinner No. 333. Apply a further 4-6 full coats until a satisfactory finish is achieved. Sand between coats using 320-400 grade paper. Remove dust with a dust wipe. Do not apply too thickly.

Hints

Mixing Stir well before use.

Thinner Spray - YTA085 Thinner No. 3. Brush - YTA333 Thinner No. 333.

Ventilation and Humidity Control Apply in dry, well ventilated conditions. Avoid damp conditions. Cold weather retards the drying and humidity can spoil the gloss.

Airless Spray Pressure: 170 bar/2500 psi. Tip Size: 0.33-0.41 mm/13-16 thou.

Conventional Spray Pressure Pot: Pressure: 3.44-4.47 bar/50-65 psi (gun pressure); 8-10 psi

(pot pressure). Tip Size: 0.89-1.4 mm/35-50 thou. Siphon Cup: Pressure: 3.44-4.47 bar/50-65 psi - gun pressure. Tip Size: 0.89-1.4 mm/35-50 thou.

Brush Always use a clean brush that is kept specifically for varnishing. Clean brushes before use.

Roller If rolling, use a thin nap roller and "tip-off" with a clean natural bristle brush.

Other Spray pressures listed are recommendations only. The applicator may use any settings which yield the best results for the individual spraying technique and current weather conditions. To enhance appearance of the bare wood and fill porous open grain, apply Interstain according to label directions and allow to dry overnight. To prevent skinning in the tin add a teaspoonful (5ml) of Thinner No. 333 on the surface before closing the lid.

Some Important Points	Never leave bare wood exposed for long periods of time as it will absorb moisture. Avoid using Schooner straight from the can as this will cause it to age prematurely and may introduce contamination to the can. Failure to follow proper dry times carefully will cause improper drying, wrinkling and loss of adhesion. Avoid painting in direct sunlight. Use above the waterline only. Only use recommended thinners. If maximum overcoating times are exceeded, sand with 280-320 grade paper. Product temperature should be minimum 10°C/50°F and maximum 29°C/85°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 29°C/85°F.
Compatibility/Substrates	Prime bare wood using Schooner thinned by 10% with Thinner No. 333. Can be used direct onto oily woods such as Teak and Iroko when thinned as for priming. Do not apply two part varnishes over Schooner.
Number of Coats	Previously varnished wood: 2-4 coats. Bare Wood: Thin first coat 10%. Then 4-6 coats
Coverage	(Practical) - 14.00 (m ² /lt) by brush, 12 m ² /lt by spray.
Recommended DFT	30 microns dry
Recommended WFT	63 microns wet
Application Methods	Brush, Roller, Airless Spray, Conventional Spray - Pressure Pot or Siphon Cup

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Schooner to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Schooner should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Schooner cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES	<i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i> X and International are registered trademarks of Akzo Nobel.
------------------------	---

Regional Addresses

Head Office
International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region
International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region
International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region
International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region
International Paint LLC
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region
International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200

