



This 2 metre diameter teak bath was primed with 2 coats of Timberseal PS epoxy timber primer to ensure that the Synacryl P acrylic-urethane varnish had the best possible adhesion to the timber. 5 coats of Synacryl P were applied followed by abrading with 1000, 1500 and 2000 grit wet and dry paper and polishing with Farecla polishing compound.