

SABA, a strong bond

Description

Deckfast MS is a one-component sealant for general use. Deckfast MS is very well suited for bonding teak decks on boards of yachts.

Solvent based adhesives

Special properties

Excellent adherence to teakwood on ship decks and bonding zones of several materials.

MSP sealants

- Continuous elastic
- No shrinkage
- Resistant to sea water en aging
- Contains no solvents

Water based adhesives

Method of use

For bonding teakwood ship decks: see system description SBS-2. Clean and dry substrate. Apply with sealant gun of air pump.

Silicone sealants

Technical data

Foam coatings

Basis	:	silane modified polymers
Consistence	:	pasty
Density	:	approx. 1310 kg/m ³
Solids content	:	approx. 98%
Skin time	:	approx. 20 minutes at 23 °C / 75% rh
Tack-free after	:	approx. 3 hours
Curing rate	:	approx. 3 mm/24 hrs at 23 °C / 75% rh
Epoxy products	Volume alteration (DIN 52451)	: < -5%
	Hardness Shore A (DIN 52451)	: 35
PU products	Module at 100% (DIN52451)	: 0.68 N/mm ²
	Tensile strength (DIN52451)	: 0.75 N/mm ²
	Elongation at break	: approx. 335 %
	Work temperature	: minimum +5 °C
Polysulfide products	Storage temperature	: minimum +5 °C, maximum 30 °C
	Temperature resistance	: approx. from -30 °C up to +80 °C
Primers	Shelf life Sausage	: 12 months in unopened packing
	Shelf life tin	: 6 months in unopened packing

Cleaning agents

Order information

Packing	Tin	Sausage
Content	5 liter	600 ml

Colour	grey RAL 7044
Article no.	100650

Safety recommendations

See the corresponding material safety data sheet.



SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, PO Box 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0) 315 658999, Fax +31 (0) 315 653207, E-mail info@saba.nl, Internet www.saba.nl.

Our application instructions and technical advice are based on our actual level of knowledge. We cannot accept any liability for conclusions and recommendations resulting from these. Buyers and/or users should judge the suitability of our products for any envisaged application by preliminary testing. The general terms and conditions for the members of the "Nederlandse Vereniging van Rubber- en Kunststoffabrikanten (NVR)" apply on all our deliveries.

Version number: 200402